

# PANEL WITH POLYISOCYANURATE (POLYURETHANE)

The Norex-H panel is a high-energy-efficient insulated metal panel that mimics the aesthetics of ACM.

## NOREX<sup>®</sup>-H

### SPECIFICATIONS

<b>DESCRIPTION</b>	<ul style="list-style-type: none"> <li>→ Horizontal &amp; Vertical Mounting</li> <li>→ Different architectural arrangements</li> <li>→ Applications: Exterior</li> </ul>		
<b>REVEAL   OPENING OPTION</b>	3/4"		
<b>WIDTH <sup>(1)(2)</sup></b>	24" , 30" , 36" or 41 1/2"		
<b>THICKNESS</b>	3" or 4"		
<b>R-VALUE</b>	<ul style="list-style-type: none"> <li>→ R8/in @ 75 °F mean temperature <sup>(4)</sup></li> <li>→ R9/in @ 35 °F mean temperature <sup>(4)</sup></li> </ul>		
<b>MAXIMUM LENGTH</b>	52' - 3"		
<b>PROFILE</b>	<ul style="list-style-type: none"> <li>→ Interior : Silkline or Grooved</li> <li>→ Exterior : Micro-ribbed, Silkline or Grooved</li> </ul>		
<b>GAUGE</b>	<ul style="list-style-type: none"> <li>→ Interior : 26, 24 or 22 ga</li> <li>→ Exterior : 26, 24 or 22 ga</li> </ul>		
<b>WEIGHT (lbs/ft<sup>2</sup>) <sup>(3)</sup></b>		<b>3"</b>	<b>4"</b>
	<b>26/26 ga</b>	2.16	2.38
	<b>24/24 ga</b>	2.66	2.88
	<b>22/22 ga</b>	3.16	3.38

### JOINT



(1) The final module width may change due to fabrication and installation tolerances. It is not recommended to design panel layouts where precise panel joint position is critical, as minor variations may occur. (2) Product availability is subject to change without notice and minimum quantities may be required for certain product configurations. For more information, please contact your local representative. (3) Calculations based on an insulated density of 2.29. (4) Results as per ASTM C518 testing and technical evaluation.

## APPLICATIONS

Norex-H panels are versatile insulated metal panels suitable for a wide range of applications, including industrial and commercial buildings, sports centers and more.

Their adaptability allows for both horizontal and vertical installations, providing design flexibility to meet various architectural requirements.

## FEATURES / BENEFITS



- Sophisticated architectural look
- Wider girt spacing reduces costs
- Fast, simple & economical installation



- Contains up to 53.8% recycled content
- Can contribute to obtaining LEED certification for a project



- No cavities, thermal bridges, or risk of interstitial condensation. Closed cell insulation
- Option : factory-applied butyl sealant in the interior and exterior joint

## FACTORY BENT CORNERS



It is possible to bend corners in factory to accommodate the corners of a building. This technique and procedure eliminates the need for surface mounted finishing trims for a seamless look.

## MAIN PHYSICAL PROPERTIES OF POLYISOCYANURATE

PROPERTY	METHOD	RESULTS
R-value/in. of thickness	ASTM C518	→ R8/in @ 75 °F mean temperature <sup>(4)</sup> → R9/in @ 35 °F mean temperature <sup>(4)</sup>
Density (lbs/ft <sup>3</sup> )	ASTM D1622	Density (pcf) 2.29
Compressive strength (psi)	ASTM D1621	13.7 PSI (3" thick sample)
Flexural strength (psi)	ASTM C203	25-30
Permeability to water vapor (perms/in.)	ASTM E96/E96M	< 2.0
Water absorption (max.)	ASTM D2842	< 1.5 %
Dimensional stability (max.)	ASTM 2126	Dimensional stability: Std dev 0.2 7 day Vol Chg @ 70 °C/97 % R.H 4.3

# TESTS / CERTIFICATIONS

	PROCEDURE	RESULTS
Fire – Canada	CAN/ULC-S101	Meets 10-minute stay-in-place requirements
	CAN/ULC-S102	Flame spread $\leq$ 25 Smoke developed $\leq$ 100  → Evaluated with steel skin
	CAN/ULC-S126	Test requirements have been met
	CAN/ULC-S134	Complies with the fire-spread and heat-flux limitations required by the National Building Code of Canada
	CAN/ULC-S138	Test requirements have been met
Fire – US	ASTM E84	Flame spread $\leq$ 25 Smoke developed $\leq$ 100  → Evaluated with steel skin
	ASTM D1929	Ignition Properties Flash Ignition Temperature : $\geq$ 600°F (316°C) Spontaneous Ignition Temperature : $\geq$ 800°F (427°C)
	FM 4880	Product approved up to 4" thick
	NFPA 259	Test requirements have been met
	NFPA 285	Test requirements have been met
	NFPA 286	Test requirements have been met
Structural	ASTM E72	See Norex Deflection Chart
	FM 4881	See FM Wall load Chart
Thermal performance	ASTM C518	→ R8/in @ 75 °F mean temperature <sup>(4)</sup> → R9/in @ 35 °F mean temperature <sup>(4)</sup>
	ASTM C1363	U-value (BTU/h*F*ft <sup>2</sup> ) 3" .0476 4" .0364
	NRCAN / DOE	Complies with Amend 14 and Title 10 / Chapter II / Subchapter D / Part 431 / Subpart R
Air infiltration	ASTM E283	Test requirements have been met
	ASTM E330	Test requirements have been met
	CAN/ULC-S741	Test requirements have been met
	CAN/ULC-S742	Test requirements have been met
Water infiltration	ASTM E331	Test requirements have been met
	AAMA 501.1	Test requirements have been met

Product availability is subject to change without notice and minimum quantities may be required for certain product configurations. For more information, please contact your local representative. All specifications provided in this document are current at the time of printing. Per Norbec Architectural's commitment to continuous product improvement, we reserve the right to modify specifications at any time without prior notice. The latest version can be found on the website. Norbec.com – 1 877 667-2321

QAI LISTING NO : B1096-1